

A COATING


Measured curve for StockOptics & BeamTuning

Material: S-LAH64

Wavelength: 400 - 600 nm

Date: 21.03.2019

Measuring Instrument: PerkinElmer UV WinLab Data Processor and Viewer Version 1.00.00



asphericon GmbH

Stockholmer Str. 9 | 07747 Jena
Germany



+49 (0) 3641 - 3100 560



+49 (0) 3641 - 3100 561

asphericon, Inc.

8586 Potter Park Drive
Sarasota, FL 34238 | USA



+1 - 941 - 564 0890



www.asphericon.com



sales@asphericon.com

asphericon, s.r.o.

Miliřská 449 | Jeřmanice 463 12
Czech Republic



+420 488 100 300